



# AQURON® 1200

PROVEN SINCE 1985

## STONE PRESERVATIVE TREATMENT

### MANUFACTURERS

**Aquron Corporation**  
P.O. Box 758  
Rockwall, Texas 75087  
(800) 342-4649 Toll Free Telephone  
(888) 412-1543 Toll Free FAX  
(972) 412-4649 Telephone  
(972) 412-1543 FAX

### PRODUCT DESCRIPTION

**Aquron® SPT-1200** is a clear, penetrating preservative treatment solution.

### BASIC USE

**Aquron® SPT-1200** is a clear, penetrating preservative treatment solution designed for sealing and preserving brick, slate, natural stone, stucco, concrete and other masonry. **Aquron® SPT-1200** is a water borne water proofing repellent that provides a tough breathing type water barrier beneath and to the surface. **Aquron® SPT-1200** helps keep surfaces clean while preserving the natural appearance of the masonry and concrete.

**Aquron® SPT-1200** conditions surfaces for subsequent applications of paint, stains, coatings, adhesives etc. **Aquron® SPT-1200** retards or eliminates efflorescence, and its application resists cracking and spalling of vertical and horizontal surfaces from successive freeze thaw cycles.

The use of **Aquron® SPT-1200** will enhance surface traction (as well as the bonding quality of paints and other topicals)

**Aquron® SPT-1200** is non-polluting, non-toxic, non-flammable, and user friendly.

### SOME ATTRIBUTES

- Stays pliable
- Waterproofs surface
- Improves traction
- Resists freeze/thaw spall-off
- Abrasion resistant
- Makes ice removal easier
- Resist fungus and mildew
- Conditions surface for topicals
- Retards or eliminates efflorescence
- Hydrocarbon resistant

### PRECAUTIONS

Spills or spray droplets in contact with glass or any area not specified to be treated should be removed immediately with water and cloth or brush. DO NOT ALLOW TO DRY. Dried product is very difficult to remove.

### COMPOSITION

**Aquron® SPT-1200** is an aqueous resin silicate that waterproofs, hardens, preserves, and is a breathable barrier in natural stone, slate, concrete, and other masonry.

### APPLICABLE STANDARDS

**Aquron® SPT-1200** meets or exceeds the following standards:

- ASTM C-67 Section 7 Water absorption
- ASTM-67 Section 9 Suction
- ASTM C-67 Section 10 Efflorescence
- ASTM C-666 Freeze-thaw resistance
- ASTM C-23-69 Artificial weathering
- ASTM C-666 Salt attack resistance
- AASHTO T259-78 Chloride ion penetration
- VOC/VOS Compliant

### PHYSICAL PROPERTIES

Physical . . . . .	liquid
Color . . . . .	clear
Odor . . . . .	slight
Specific gravity . . . . .	1.02±
Weight per gallon . . . . .	3.83kg/8.46lbs
Boiling point . . . . .	230°F/110°C
pH . . . . .	8±
Solvent . . . . .	water
Flash point . . . . .	none
Toxicity . . . . .	none
Freeze temperature . . . . .	32°F/0°C
Hazardous vapors . . . . .	none
Environmentally . . . . .	neutral
Shelf life . . . . .	indefinite
Freeze harm . . . . .	absolute
Flammability . . . . .	none
VOC/VOS compliant . . . . .	yes
Resistance to UV . . . . .	excellent
Paintable . . . . .	yes
Waste disposal methods . . . . .	non-hazardous
Equipment cleaning solvent . . . . .	mild soap & water

# ■ INSTALLATION

## JOB CONDITIONS

1. Do not proceed with application of **Aquron® 1200** when ambient temperature and/or substrate temperatures are less than 50°F/10°C or forecasted to drop below 50°F/10°C during the next 6 hours.
2. Do not apply **Aquron® 1200** in rainy conditions or when rain is expected within 24 hours.
3. Should temperature be extremely hot, application should be made at late night or early morning.
4. Caution should be taken in windy conditions as **Aquron® SPT-1200** if allowed to dry on glass or any area not specified to be treated is very difficult to remove. (Remove immediately with water and cloth or brush).

## APPLICATION PROCEDURE

1. Coverage Rate

### TYPE OF SURFACE

	ft <sup>2</sup> /GAL	m <sup>2</sup> /L
Limestone	200-300	4-7m <sup>2</sup>
Adobe	250-350	5-8m <sup>2</sup>
Brick	300-550	7-13m <sup>2</sup>
Grout	350-700	8-16m <sup>2</sup>
Plaster	350-550	8-13m <sup>2</sup>
Stucco	200-450	7-12m <sup>2</sup>
Concrete Brick	200-300	4-7m <sup>2</sup>
Man-made Stone	250-450	5-10m <sup>2</sup>
Slate	400-500	9-12m <sup>2</sup>
Clay Tile	400-600	9-14m <sup>2</sup>
Concrete	300-450	7-10m <sup>2</sup>
Pavers	300-400	7-9m <sup>2</sup>

2. Application is to be made with low pressure spray equipment with tip size of .026 to .072. DO NOT ATOMIZE (use pump-up garden sprayer with fan tip).
3. Holding tip 6"-12"/150-300mm from surface using overlapping spray pattern and fanning motion at the end of each horizontal pass.
4. Entire area being treated is to be saturated, but do not allow **Aquron® SPT-1200** to puddle, if so disperse puddled area with broom 1-4 hours after application is completed (do not allow puddles of **Aquron® SPT-1200** to dry as whitening effects may occur).

## WARRANTIES AND LIMITATIONS OF LIABILITY

Aquron Corporation ("Seller") warrants that if any goods supplied prove defective in workmanship or materials, that Seller shall replace them or refund their purchase price. Aquron Corporation offers a performance warranty for its **Aquron® SPT-1200** product. This warranty for the performance of **Aquron® SPT-1200** must be requested from the Aquron Corporation and initiated prior to applying **Aquron® SPT-1200**. Failure to initiate warranty of performance prior to application, holds harmless Aquron Corporation of any liability arising from its use, and user assumes all risk and liabilities whatsoever in connection therewith. The terms of this paragraph may not be orally modified. There are no warranties express or implied which extend beyond the face herewith.

5. Precautions should be taken to cover any areas not intended to be sprayed, as dried product is difficult to remove. Should overspray or accidental contact be made, remove product with water and brush or cloth before it dries.
6. Depending on temperature and other weather conditions, **Aquron® SPT-1200** will normally dry in 12-24 hours at 70°F/21°C.

## CLEAN-UP & SAFETY

No special clothing, breathing apparatus, goggles or gloves are necessary but in enclosed areas it is advisable to wear a suitable respirator to avoid possible irritation to breathing.

**Attention should be made to watches, spectacles or eye-glasses etc., as Aquron® SPT-1200 once dried is difficult to remove!**

Clean equipment using water and mild soap. Never store spray equipment without cleaning and following manufacturer's recommendations for storage between usage.

## SHELF LIFE

Shelf life is indefinite provided containers are kept tightly sealed when not in use.

## PACKAGING

**Aquron® SPT-1200** is available in 5 gallon/18.9 liters and 55 gallon/208.2 liters drum size. **Aquron® SPT-1200** is also available in bulk containers.

## MAINTENANCE

Special maintenance of treated area is not required.

## TECHNICAL SERVICES

Technical information and assistance may be obtained from your local dealer, or by calling the technical department of the Aquron Corporation at (972) 412-4649, (800) 342-4649 Office, or (972) 412-1543 FAX or toll free FAX (888) 412-1543.

## LOCAL AREA REPRESENTATIVE